

## Low GDD Ultrafast Laserline Mirror

Coating code: 515UFLL45DEG

Coating specification:  $R_s > 99.95\%$  &  $R_p > 99.9\%$  @ 500-530nm, AOI 45°

GDD:  $|GDD R_s| < 20 \text{ fs}^2$ ,  $|GDD R_p| < 20 \text{ fs}^2$


LDT:

> 0.15 J/cm<sup>2</sup>, 515 nm, 500 fs, 10 kHz, p-pol

> 0.3 J/cm<sup>2</sup>, 515 nm, 500 fs, 10 kHz, s-pol

> 0.8 J/cm<sup>2</sup>, 515 nm, 10 ps, 10 kHz, p-pol

> 1.3 J/cm<sup>2</sup>, 515 nm, 10 ps, 10 kHz, s-pol



## Low GDD Ultrafast Laserline Mirror

Coating code: 515UFL45DEG

Coating specification:  $R_s > 99.95\%$  &  $R_p > 99.9\%$  @ 500-530nm, AOI 45°

GDD:  $|GDD R_s| < 20 \text{ fs}^2$ ,  $|GDD R_p| < 20 \text{ fs}^2$

